

Cold-mix bitumen repair bags

PRODUCT GUIDE · CHEMICAL-20

Bagged cold-mix asphalt for repairs within the selected product's application limits.

Application

Suitable pothole and pavement patching tasks.

Cold-mix bitumen repair bags — reference specifications

Reference product	Dingo Bitumen, 20 kg bag
Pack size	20 kg bag; shown pack identity is Dingo Bitumen.
Typical uses	Potholes, driveways, paths, speed humps and general repairs.
Coverage	60 kg covers approximately 1 m ² at 23 mm depth.
Layer and repair depth	Maximum 30 mm per application; this compacts to about 25 mm. Repairs thicker than 50 mm are not recommended.
Substrate and placement	Use a dry area and thoroughly compacted base. Spread evenly, leave a few minutes, then compact with a roller, plate compactor or hand tamper.
Return to traffic	PDS permits immediate traffic following placement/compaction and recommends a light sand covering for immediate use.
Curing limitations	Hardens over several weeks depending on application and weather; avoid scuffing during this period and avoid sealers/coatings for 6 months.

These properties describe the identified reference product. Confirm the selected model, sizes, inclusions and suitability with the quotation and current manufacturer documents.

Details to include in your enquiry

Repair area depth and surface · Bag size and product specification · Quantity and delivery

Technical references

[Product data sheet — July 2025 — open reference](#) · Product data sheet · Confirm current revision with quotation

[Safety data sheet — open reference](#) · Safety data sheet · Confirm current revision with quotation

Reference values apply only to the identified configuration. The offered model, dimensions, approvals and lead time are confirmed with your quote. Availability is subject to confirmation.