

Bitumen paint

PRODUCT GUIDE · CHEMICAL-26

Bituminous paint for compatible protective-coating applications.

Application

Documented coating tasks on suitable substrates.

Bitumen paint — reference specifications

Reference product	Crommelin BLACKSEAL HEAVY DUTY Bitumen Waterproofing Membrane, 15 L
Pack sizes	1 L, 4 L and 15 L pails; pictured pack is 15 L.
Preparation by use	For bitumen paint, dilute 50:50 with water. As waterproofing membrane, stir and apply undiluted.
Substrates	Concrete/masonry, terracotta, cement sheet, aluminium/steel, timber posts and plywood; clean, dry and sound.
Exposure limits	Below ground or otherwise protected from UV. Not suitable for painting, tiling or overcoating.
Application conditions	Recommended 10–35°C; maximum 85% RH during application and initial cure.
Membrane-mode coverage	Undiluted membrane: minimum 2 coats at 1.5 m ² /L per coat; 15 L gives approximately 11.25 m ² finished coverage. This is not a diluted-paint coverage claim.
Membrane recoat and cure	Recoat when touch dry/black, approximately 2–4 hours. Dry backfill after at least 72 hours; full cure 7 days. Keep dry until fully cured.

Bitumen-paint dilution and undiluted waterproofing-membrane use are different applications. The listed coverage and cure values are explicitly for membrane mode; follow the selected use in the current technical sheet.

Details to include in your enquiry

Substrate and exposure · Required formulation and coated area · Container size and quantity

Technical references

[Technical data sheet — November 2022 — open reference](#) · Product data sheet · Confirm current revision with quotation

[Safety data sheet — includes Blackseal and Water Based Bitumen Paint — open reference](#) · Safety data sheet · Confirm current revision with quotation

Reference values apply only to the identified configuration. The offered model, dimensions, approvals and lead time are confirmed with your quote. Availability is subject to confirmation.